

3340H

Polypropylene (PP)

Description:

3340H is a Random Copolymer Polypropylene resin for extrusion sheet and molding process with high clarity. It is suitable for cosmetic bottles, sheet for thermoforming, closure, and file. It also meets the F.D.A. requirement in the code of federal regulations in 21 CFR 177.1520 for food contact.

Typical applications:

Extrusion sheet : sheet for thermoforming, sheet, files
 Blow molding : cosmetic bottles
 Injection molding: closure

Physical Properties:	Method	Unit	Value
Melt Flow Index (2.16 kg/230°C)	ASTM D1238	g/10min.	2
Tensile Strength at Yield	ASTM D638	N/mm ²	29.5
Elongation at Yield	ASTM D638	%	38
Charpy Notched Impact Strength (at 23°C)	DIN 53453	mJ/mm ²	11
Flexural Modulus (1% SECANT)	ASTM D790	MPa	1000
Rockwell Hardness	ASTM D785	R-Scale	90
Heat Distortion Temperature (Load 0.45 N/MM²)	ASTM D 648	°C	83

Processing Technique

Processing Temperature : 170 – 230 °C

However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.*

Remark: The values presented on the above are typical laboratory average, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitable of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.